

FERRO ANGOLARE													
	3	4	5	6	7	8	9	10	12	14	15	18	
15	■												15
20	■	■											20
25	■	■	■										25
30	■	■	■	■									30
35	■	■	■	■									35
40	■	■	■	■									40
45		■	■	■									45
50		■	■	■	■								50
55			■	■									55
60			■	■		■		■					60
65				■	■	■							65
70			■	■	■	■	■						70
75			■		■	■							75
80				■		■	■	■					80
90							■						90
100						■		■	■				100
110								■					110
120								■	■				120
130								■	■	■			130
140									■		■		140
150									■		■		150
180											■		180
200												■	200
	3	4	5	6	7	8	9	10	12	14	15	18	

S 275 JR ( FE 430 B )

 ANCHE ZINCATO

**TABELLA PESO TEORICO SEGUE A PAGINA 2**

FERRO ANGOLARE KG. / ML.													
	3	4	5	6	7	8	9	10	12	14	15	18	
15	0,64												15
20	0,88	1,14											20
25	1,12	1,46	1,78										25
30	1,36	1,78	2,18	2,56									30
35	1,60	2,09	2,57	3,04									35
40	1,84	2,42	2,97	3,52									40
45		2,74	3,38	4,00									45
50		3,06	3,77	4,47	5,15								50
55			4,18	4,95									55
60			4,57	5,42		7,09		8,69					60
65				5,91	6,83	8,62							65
70			5,37	6,38	7,38	8,36	9,34						70
75			5,78		7,94	9,03							75
80				7,34		9,63		11,90	14,00				80
90							12,20						90
100						12,20		15,00	17,80				100
110								16,60					110
120								18,20	21,60				120
130								19,80	23,60	27,20			130
140									25,60		31,40		140
150									27,30		33,80		150
180											41,00		180
200												54,30	200
	3	4	5	6	7	8	9	10	12	14	15	18	



**PER ZINCATURA CALCOLARE 8% IN PIU'**